

## Rubber Sheet

### FDA White Nitrile Sheet

**General Properties:**

- Excellent resistance to petroleum-based fluids
- Good physical properties

**Specifications:**

- Common Name: Nitrile, Buna-N
- Food grade
- Polymer: Nitrile-Butadiene
- ISO/ASTM Designation: NBR



Style	ASTM Specification (SI units)	Temp. Range (°F)	Durometer (Shore A)	Tensile Strength (PSI)	Elongation (%)	Finish
SBSWNR60	D 2000 M1BG 608	-31 to +230	55 – 65	1100	400	Plate

### Black Cloth-Inserted SBR Sheet

**General Properties:**

- Excellent physical properties

**Specifications:**

- Common Name: Cloth-reinforced Black Rubber Sheet
- Commercial grade with cloth reinforcement
- Polymer: Styrene-Butadiene rubber reinforced with 3.4 oz./sq. yd. nylon fabric
- ISO/ASTM Designation: SBR



Style	ASTM Specification (SI units)	Temp. Range (°F)	Ply	Durometer (Shore A)	Tensile Strength (PSI)	Finish
SBSC11	D 2000 M2AA 603	-20 to +170	1	55 – 65	600	Plate
SBSC12	D 2000 M2AA 603	-20 to +170	2	55 – 65	600	Plate
SBSC13	D 2000 M2AA 603	-20 to +170	3	55 – 65	600	Plate
SBSC14	D 2000 M2AA 603	-20 to +170	4	55 – 65	600	Plate

### Black SBR Sheet

**General Properties:**

- Good physical properties

**Specifications:**

- Common Name: Black Rubber Sheet
- Commercial grade
- Polymer: Styrene-Butadiene
- ISO/ASTM Designation: SBR



Style	ASTM Specification (SI units)	Temp. Range (°F)	Durometer (Shore A)	Tensile Strength (PSI)	Elongation (%)	Finish
SBSBL60	D 2000 M1AA 604	-13 to +158	60 – 70	600	200	Plate