

Red SBR Sheet Plate & Fabric Finish

General Properties:

- Good physical properties

Specifications:

- Common Name: Red Rubber Sheet
- Commercial grade
- Polymer: Styrene-Butadiene
- ISO/ASTM Designation: SBR
- Meets D1330 Grade 1



Style	ASTM Specification (SI units)	Temp. Range (°F)	Durometer (Shore A)	Tensile Strength (PSI)	Elongation (%)	Finish
SBSR70P	D 2000 M1AA 705	-22 to +158	65 – 75	600	200	Plate
SBSR70F	D 2000 M1AA 705	-22 to +158	65 – 75	600	200	Fabric Impression

Viton® Sheet

General Properties:

- Excellent resistance to many concentrated acids
- Excellent resistance to heat

Specifications:

- Common Name: Viton®
- Commercial grade
- Polymer: Hexafluoropropylene Vinylidene Fluoride
- ISO/ASTM Designation: FKM



Style	ASTM Specification (SI units)	Temp. Range (°F)	Durometer (Shore A)	Tensile Strength (PSI)	Elongation (%)	Finish
SBSVI70	D 2000 M1HK 704	-14 to +482	72	600	165	Plate

CSM Sheet

General Properties:

- Excellent resistance to oxidation and outstanding resistance to strong sunlight and ozone
- Good resistance to general acids, oils and greases

Specifications:

- Common Name: CSM
- Polymer: Chlorosulphonated Polyethylene
- ISO/ASTM Designation: CSM



Style	ASTM Specification (SI units)	Temp. Range (°F)	Durometer (Shore A)	Tensile Strength (PSI)	Elongation (%)	Finish
SBSCSM60	D 2000 M1CE 614	-31 to +257	55 – 65	1400	350	Plate